



PRODUCT DATA SHEET

layflat SBS®



LF60P

Base & Ply Membrane
SBS Modified Bitumen
Polyester Reinforced



USAGE: Base / Ply
 APPLICATION: Hot Asphalt, Cold Adhesive Mechanical
 PACKAGING: Paper Wrapped
 25 rolls/pallet



	UNIT	STANDARDS		MBTECHNOLOGY NOMINAL	
		ASTM-D6164 Grade S			
		Type 1	Type 2		
Reinforcement	-	Polyester Mat (Non-Woven, Asbestos-Free)			
Top Surfacing	-	Sand			
Bottom Surfacing	-	Sand			
Roll Coverage	Squares	1.5			
Lay Lines	inches	3 - 13 - 19			
Roll Weight	lbs			106	
Roll Length	ft + inches			49' 6"	
Roll Width	inches			39.625	
Thickness	mil	85	115	98	
Net Mass	lbs/100ft ²	54	70	64	
Tensile Peak Load @ 23°C	lbs/in	50	70	MD	96
				CD	61
Elongation at Max Load @ 23°C	%	35	50	MD	48
				CD	61
Ultimate Elongation @ 23°C	%	38	60	MD	51
				CD	65
Tear Strength @ 23°C	lbs	55	70	MD	123
				CD	91
Low Temp Flexibility (Max)	°C	-18	-18	-18	
Compound Stability (Min)	°C	102	102	102	
Dimensional Stability D5147/D1204	% max	1	1	MD & CD	< 0.85

Ultimate Elongation is reported at point where load has dropped down to 5% of its original max.

ADDITIONAL INFORMATION		
LEED	Recycled Content: 0%	Production Location: Fresno, California U.S.A.



188 S. Teilman Avenue Fresno, California 93706-1334 U.S.A.
 Toll Free: 800-621-9281 Fax: 559-233-4607 www.mbtechnology.com

WARNING: This product can expose you to chemicals including benzene, which is known to the State of California to cause cancer and birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov
ADVERTENCIA: Este producto puede exponerle a químicos incluyendo benceno, que es conocido por el Estado de California como causante de cáncer y defectos de nacimiento u otros daños reproductivos. Para mayor información visite www.P65Warnings.ca.gov

