## layfastSBS® Underlayment/Base



**USAGE:** Underlayment / Base

> Tile, Shingle, Shake and Metal (excluding copper & zinc) Waterproof base for torch down APP, SBS & BUR system

APPLICATION: Mechanical

Secure with 1" Head Nails / Staples shall not be used

Paper Wrapped PACKAGING:





layfast SBS ® CERTIFIED TO: ASTM D226, ASTM D4601, ASTM D4869 Class A Fire Classification per ASTM E108





| 36 rolls/pallet   |                         | STANDARDS  |         |       |         |           |        |        |       |          |          |  |
|---|-------------------------|--|---------|-------|---------|-----------|--------|--------|-------|----------|----------|--|
|   | UNIT                    | ASTM   |         | ASTM  |         | ASTM      |        | ASTM   | ICC   | MBTECHI  | NOLOGY   |  |
| ONI   |                         | D2   |         | D4    |         | D48       |        | D6757  | AC165 | NOM      | INAL     |  |
|   |                         |  |         |       | Type 2  | Type 3    | Type 4 | Type 2 | -     |          |          |  |
| Reinforcement   | -                       | Fibe   | erglass | Mat   | (Asbest | tos-Free) |        |        |       |          |          |  |
| Top Surfacing   | ı                       | San  | d       |       |         |           |        |        |       |          |          |  |
| Bottom Surfacing  | -                       | San  | d       |       |         |           |        |        |       |          |          |  |
| Accumulated Time of Exposure (max)  | Days                    | 90 However, MBT reccomends that <i>layfast SBS®</i> be covered by an approved roof covering as soon as possible. |         |       |         |           |        |        |       |          |          |  |
| Roll Coverage   | Squares                 | 1  |         |       |         |           |        |        |       |          |          |  |
| Lay Lines   | inches                  | 2 - 4 - 6 - 19   |         |       |         |           |        |        |       |          |          |  |
| Roll Weight   | lbs                     | -  |         |       |         |           | 68     |        |       |          |          |  |
| Roll Length   | ft + inches             | -  |         |       |         |           | 32' 6" |        |       |          |          |  |
| Roll Width  | inches                  | -  |         |       |         |           |        | 39.75  |       |          |          |  |
| Thickness   | mil                     | -  |         |       |         |           | 83     |        |       |          |          |  |
| Net Mass  | lbs/100ft²              | 11.5   | 26      | 13.4  | 15.5    | 20        | 26     | -      | 15.5  | 63       |          |  |
| Breaking Strength @ 23°C MD   | lbs/in                  | 30   | 40      | 22    | 44      | 40        | 40     | -      | 40    | MD       | 78       |  |
| Breaking Strength @ 23°C CD   | lbs/in                  | 15   | 20      | 22    | 44      | 20        | 20     | -      | 40    | CD       | 57       |  |
| Pliability  | ½" Radius               | Shall Not Crack  |         |       |         |           |        |        |       |          | Pass     |  |
| Filability  | ¾" Radius               | Stidil NUL Clack   |         |       |         |           |        |        |       | MD & CD  | Pass     |  |
| Loss on Heating @ 105°C for 5 hours   | % max                   | 4  | 4       | -     | -       | 6         | 6      | 4      | 4     | ≤ 0.30   |          |  |
| Moisture @ Time of Manufacture  | % max                   | 4.3  | 4.1     | 1     | 1       | 2         | 2      | -      | 1     | ≤ 0.40   |          |  |
| Liquid Water Transmission   | 4 hrs min               | -  | ı       | -     | -       | Pass      | Pass   | Pass   | Pass  | Pass     |          |  |
| Mass of Desaturated Glass Mat   | lbs/100ft²              | -  | ı       | 1.4   | 1.7     | -         | -      | -      | 1.7   | ≥ 1.70   |          |  |
| Ash of Glass Mat Only   | %                       | -  | -       | 70-88 | 70-88   | -         | -      | -      | 70-88 | Pass     |          |  |
| Dimensional Stability D5147/D1204   | % max                   | -  | -       | -     | -       | -         | -      | -      | -     | MD & CD  | < 0.12   |  |
| Dimensional Stability F1087   | % max                   | -  | •       | -     | -       | 1.75      | 1.75   | 1.65   | 1.65  | MD & CD  | < 0.12   |  |
| Resistance to Growth of Mold D3273  | % max                   | -  | •       | -     | -       | -         | -      | -      | -     | No Funga | I Growth |  |
| Water Vapor Transmission E96 Proc A  * Meets Class   Vapor Retarder as defined by the IBC | Permeance<br>(US Perms) | -  | -       | -     | -       | -         | -      | -      | -     | ≤ 0.02   | 26 *     |  |

Meets Class I Vapor Retarder as defined by the IBC

| ADDITIONAL INFORMATION |                      |  |  |  |  |  |  |
|------------------------|----------------------|--|--|--|--|--|--|
| LEED                   | Recycled Content: 0% | Production Location: Fresno, California U.S.A. |  |  |  |  |  |



188 S. Teilman Avenue Fresno, California 93706-1334 U.S.A. Toll Free: 800-621-9281 Fax: 559-233-4607 www.mbtechnology.com



